



## SICO MAGNESIUM OXIDE (CALCINED MAGNESITE)

min. 92% MgO (54% Mg)

## 1/ DESCRIPTION

MgO 27 is a caustic calcined natural magnesite with a moderate activity. The low level of impurities make this product suitable for different applications such as: fertiliser and water treatment. Due to the high bioavailability of the Mg in this product, it is specially suited for feed formulation and premixes.

## 2/ COMPOSITION

	Typical	Specification
Magnesium Oxide (MgO) % (ignited)	93.25	min. 92.00
Calcium Oxide (CaO) %	1.80	max. 3.00
Silica (SiO <sub>2</sub> ) %	2.60	max. 4.00
Aluminium Oxide (Al <sub>2</sub> O <sub>3</sub> )	0.22	max. 0.40
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) %	0.70	max. 1.00
Sulphate (SO <sub>3</sub> ) %	0.22	max. 0.30
Loss on ignition %	5.00	max. 7.50
Total heavy metals ppm	10.00	
3/ PHYSICAL PROPERTIES		

Screen size, mm Bulk density, g/l Colour 0.2 - 0.8 950 light brown to white

## 4/ PACKING

- 25 kg polypropylene bags on shrinkwrapped pallets

- big bags

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. Sap International cannot accept any responsibility for loss or damage or infringement of patent rights that may result from the use of information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of the products with their own tests. Any dimensions shown are approximate.

Any information in this publication is believed to be accurate and is given in good faith, but is for the customer to satisfy himself of the suitability for his own particular purpose. No representation, warranty or guarantee is made to its accuracy, reliability or completeness.

