



**PRODUCT INFO
& DATASHEET**

ZEOLITE FARM / FEED

12/2016

1/ PRODUCT SPECIFICATIONS

Product name : Natural Zeolite, type Clinoptilolite of sedimentary origin
Empirical formula : (Ca,K₂,Na₂,Mg)₄Al₈Si₄₀O₉₆.24H₂O
 Chemical name : Hydrated calcium aluminosilicate.
Chemical type : Molecular sieve
CAS No. Natural Zeolite 1318-02-1
CAS No. Clinoptilolite 12173-10-3
EC No. 215-283-8

2/ CHEMICAL COMPOSITION

Silicon Dioxide SiO₂	64.18-75.50%	Sodium Oxide Na₂O	0.10-2.97%
Aluminum Oxide Al₂O₃	10.93-14.80%	Titanium Dioxide TiO₂	0.08-0.39%
Calcium Oxide CaO	1.43-11.68%	Phosphorus Oxide P₂O₅	0.01 – 0.18%
Kalium Oxide K₂O	1.24-4.24%	Iron Oxide FeO	0.29-1.43%
Iron Oxide Fe₂O₃	0.12-2.45%	Sulfur Oxide SO₃	0.00-0.23%
Magnesium Oxide MgO	0.29-1.43%	L.O.I. Humidity	max. 6%
			SI/AI 4.8 – 5.4

3/ PHYSICAL COMPOSITION

Clinoptilolite	82 - 84%	Plagioclase	3 - 4%
Cristobalite	9%	Quarz	traces
Clay mica	2 - 3%	Dioxins & - PCB's	max. 1.5 ng 2,3,7,8-TCDD TEQ/kg Tested on heavy metals and salmonella

4/ PHYSICAL-MECHANICAL DATA

Softening point	1 260 0C	Porosity	24 - 32 %
Melting point	1 340 0C	Effective diameter of pores	0.4 nm (4 angstrom)
Pour point	1 420 0C	Compactness	70%
Compression strenght	33 MPa	Whiteness	70%
Specific weight	750-950kg/m ³	Mohs hardness	2 - 3
Volume weight	1333-1176L	Grindability according to VTI	kVTI = 1,628
Appearance & smell	grey-green-without smell	Water Absorption	34 - 36 %
		pH	6.8 – 7.2

5/ ION EXCHANGE PROPERTIES

Total exchange	Ca ²⁺ 0,64 - 0,98 mol/kg Mg ²⁺ 0,06 - 0,19 mol/kg	K ⁺ 0,22 - 0,45 mol/kg Na ⁺ 0,01 - 0,19 mol/kg min. 0,70 mol/kg
Partial exchange capacity NH₄⁺		1,2 - 1,5 mol/kg
Total exchange capacity NH₄⁺		
Sorption of steam by dehydrated rock	at relative humidity of 52 % at relative humidity of 98 %	7,5 - 8,5 g H ₂ O/100g 13,5-14,5 g H ₂ O/100g

Any information in this publication is believed to be accurate and is given in good faith, but is for the customer to satisfy himself of the suitability for his own particular purpose. No representation, warranty or guarantee is made to its accuracy, reliability or completeness.

SAP INTERNATIONAL CORPORATION bvba Krekelenberg 69, B-2980 Zoersel, Belgium
 Tel. +32-3-309.06.51 Fax. +32-3-309.19.31 Email : info@sico.be Website : www.sico.be

SICO FEEDS
 EVERY TIME THE *right* SOLUTION